

TECH DATA SHEET

PROJOINTTM PORCELAIN ULTIMATE PAVING PRIMER



PREPARATION:

PROJOINT PORCELAIN PRIMER should be mixed with 2.8 litres of cold clean water per 10kg bag.

- CLEANING**
 All tools should be washed out with water immediately after use. Waste material should not be emptied into drainage systems.
- 1: Remove the bags from the tub and add the water to the bucket.
 - 2: Add the powder slowly and mix using a drill and paddle/plasterers' whisk.
 - 3: Mix for 2 minutes.
 - 4: Leave to stand for 2 minutes. This is important as the process allows the polymer additives to dissolve and activate.
 - 5: Re-mix for a further 2 minutes.

APPLICATION INSTRUCTIONS:

6: When wearing appropriate PPE, apply a thorough and even coat of the primer as a slurry using a masonry brush or roller to the underside of the paving. The pot life of the mixed slurry is approximately 60 minutes at 20°C.

The primer should be completely dry prior to laying the paving. Depending on the temperature and moisture, the primer will be dry within 10 to 15 minutes, however the primed slabs can be left undercover and dry for up to 2 weeks prior to laying. Paving should then be laid on a wet sand and cement mortar bed.

PORCELAIN PRIMER is designed to be applied to the underside of porcelain paving and other low absorption substrates to promote adhesion. The underside of the paving should be clean, dry and free of any material which may impair adhesion.

Do not apply to shiny surfaces. PROJINT PORCELAIN PRIMER should not be used in wet weather and/or if frost is forecast within 24 hours of application. Suitable for use in temperatures between 3°C and 25°C.



HEALTH AND SAFETY ADVISORY

APPLICATION IMAGERY

HAZARD STATEMENTS: H301 Harmful if swallowed. H315 Causes skin irritation. H317 May cause an allergic skin reaction. H318 Causes serious eye damage. H335 May cause respiratory irritation.

PRECAUTIONARY STATEMENTS: P280 Wear protective gloves/protective clothing/eye protection/face protection. P301+312 IF SWALLOWED: call a poison centre/doctor if you feel unwell. P302+352 IF ON SKIN: wash with plenty of water. P304+340 IF INHALED: remove person to fresh air and keep comfortable for breathing. P305+351+338 IF IN EYES: rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. P310 Immediately call a poison centre/doctor.

A FULL SAFETY DATASHEET IS AVAILABLE ON REQUEST

SYSTEM	HIGH PERFORMANCE SLURRY PRIMER FOR PORCELAIN AND NATURAL STONE PAVERS
STORAGE	STORE IN A COOL, DRY, AND FROST FREE ENVIRONMENT AT TEMPERATURES BETWEEN 5°C AND 30°C
SHELF LIFE	12 MONTH FROM DATE OF MANUFACTURE
PACKAGING	20KG TUBS DELIVERED ON SHRINK - WRAPPED PACKAGING
PALLET QUANTITY	44 UNITS
COVERAGE	AS SHOWN ON COVERAGE TABLE
COLOURS	N/A
WALK ON CURING TIME	12 HOURS IN DRY AMBIENT CONDITIONS
FULL STRENGTH	28 DAYS
SUB BASE REQUIREMENT	FULL SOLID BED

KEY FACTS:

- ✓ ENABLES PORCELAIN PAVING TO BE LAID ON SAND AND CEMENT BEDDING
- ✓ ONE COAT APPLICATION TO THE UNDERSIDE OF PAVING
- ✓ EXCELLENT WORKABILITY AND ADHESION PROPERTIES
- ✓ PRE-PRIMED PORCELAIN SLABS CAN BE LAID TWO WEEKS AFTER APPLICATION OF PRIMER

'High performance priming slurry for porcelain paving...'

BRUTE STRENGTH PAVING PRODUCTS

